

## BARBOTEX

FINE TEXTURED PAINT

Ref.:1440

### TECHNICAL IDENTIFICATION

Water based fine texture Paint based on a 100% pure acrylic binder.

### AREA OF USE

To be applied on exterior walls when a fine textured finish is needed. Is also recommend when micro cracks are present.

### PROPERTIES

- Fine sanded appearance.
- High layer thickness per coat.
- Disguises static micro cracks.
- Exceptional resistance to weathering, alkalis and liquid water.
- Good permeability to water vapour.

### PHYSICAL CHARACTERISTICS

(Referring to White)

- Colour	Can be tinted using the Barbomix System
- Features of dry film	Matt /Textured.
- Volume solids	47 ± 2%
- Practical coverage	4 to 6 m <sup>2</sup> / L / coat (depending on substrate and application conditions).
- Drying time	
Touch dry	2 to 4 hours.
Recoat	6 hours minimum.
- Flash Point	Non-flammable
- Volatile Organic Compounds (VOC)	EU limit value for this product (Cat. A/c): 40 g/L (2010). This product contains max. 30 g/L VOC.*

---

## APPLICATION CONDITIONS

---

- <b>Preparation of surface</b>	Surfaces must be dry and free from dust, grease and loose particles. Cracks and other irregularities must be repaired in advance.
• <b>First painting</b>	After brushing and cleaning the surface, first apply PRIMÁRIO BARBOLITE diluted up to 5% with Diluente 1425, or ISOLANTE ISOCRIL diluted up to 50% with Diluente 1425.
• <b>Recoat</b>	Remove dust and loose paint and then paint like a first painting. If the surface is contaminated with fungi and/or algae, disinfect the surface with SOLUÇÃO DE LIMPEZA BLOCHOQUE and then paint like a first painting.
- <b>Environmental conditions</b>	Ambient temperature – Above 5 °C Relative humidity – Below 80% Substrate humidity – Below 5% Substrate temperature – 2 to 3 °C above dew point

---

## APPLICATION INSTRUCTIONS

---

- <b>Product preparation</b>	Stir until fully homogenised.
- <b>Application processes</b>	Brush or roller.
- <b>Thinners and dilution ratio</b>	Dilute with water up to 5% for 1st coat and no dilution for the 2nd coat.
- <b>Drying time between coats</b>	6 hours.
- <b>Number of coats</b>	2 to 3 coats.
- <b>Cleaning solvent</b>	Water.
- <b>Available packaging</b>	5 and 15L.

---

## STORAGE STABILITY

Minimum Temperature – 5 °C  
Maximum Temperature – 35 °C

---

## RISKS AND SAFETY

See safety data sheet at [www.barbot.pt](http://www.barbot.pt)

---

**October 2015**

(replaces the May 2013 specifications)

---

The characteristics of this product may be altered without prior notice due to the continuous research and development policy at Barbot – Indústria de Tintas, S.A. This information is based on our current knowledge of the product, however since conditions of use are beyond our control, we give no guarantee of results.



**BARBOT**

BARBOT - Indústria de Tintas, S.A.  
Rua dos Bombeiros, 466  
4410-295, Canelas, Vila Nova de Gaia  
tel.: 227 169 200 | fax: 227 169 218  
[www.barbot.pt](http://www.barbot.pt)