

ISOLANT ISOCRIL

SEALER FOR INTERIOR AND EXTERIOR WALLS

Ref. 2310

TECHNICAL IDENTIFICATION

Sealer based on acrylic resins.

AREA OF USE

Designed for application in all kinds of interior and exterior walls, whenever they are very porous, chalky or with intense or non even absorption.

PROPERTIES

- Alkali resistant
- Excellent adhesion even over chalky surfaces
- High penetration power
- Allows moisture transpiration
- Regularizes the surface absorption permitting a better coverage and finishing of the topcoats.

PHYSICAL CHARACTERISTICS

- Colour	Transparent
- Volume solids	9± 2%
- Spreading Rate	8 to 12 m ² /L
- Flash point	Non-flammable
-Drying Time	
• Set-to-touch	1 to 2 hours
• Overcoating	24hours.
-Volatile Organic Compounds (VOC)	EU limit value for this product (Cat. A/h): 750 g/l (2010). This product contains max. 745 g/l VOC.*

APPLICATION CONDITIONS

- | | |
|-----------------------------------|---|
| - Preparation of surface | Surfaces must be dry and free from dust, grease and loose particles. Cracks and other irregularities must be repaired in advance. |
| - Environmental conditions | Ambient temperature – Above 5 °C
Relative humidity – Below 80%
Substrate humidity – Below 5%
Substrate temperature – 2 to 3 °C above dew point |
-

APPLICATION INSTRUCTIONS

- | | |
|--------------------------------------|---|
| - Product preparation | Stir until fully homogenised. |
| - Application processes | Brush or roller. |
| - Recommended finishes | Conventional emulsion paints, textured paints or flexible paints. |
| - Solvents and dilution ratio | Dilute 40 to 50% with Diluente 1426. |
-

STORAGE STABILITY

Minimum Temperature – 5 °C
Maximum Temperature – 35 °C

RISKS AND SAFETY

See safety data sheet at www.barbot.pt

september 2013

(replaces December 2008 specifications)

The characteristics of this product may be altered without prior notice due to the continuous research and development policy at Barbot – Indústria de Tintas, S.A. This information is based on our current knowledge of the product, however since conditions of use are beyond our control, we give no guarantee of results.

