

SILICOR

TEXTURED WATER-BASED PAINT FOR EXTERIORS

Ref.:1400

TECHNICAL IDENTIFICATION

Water based textured paint made with special copolymers and pigments resistant to light and weather.

AREA OF USE

Designed for application in exterior walls when a decorative finish is wanted or to hide small substrate imperfections.

PROPERTIES

- Excellent decorative effect
- Excellent weather resistance
- Alkali resistant
- Good elasticity
- Good opacity
- Easy to apply
- Good water impermeability
- Allows "wall breathability"

PHYSICAL CHARACTERISTICS

(Referring to White)

- Colour	Can be tinted using the Barbomix System
- Gloss	Slightly satin
- Volume solids	59 ± 2%
- Practical coverage	1 to 1,5 m ² / L / coat (depending on substrate and application conditions)
- Drying time	2 to 6 hours

APPLICATION CONDITIONS

- Preparation of surface

Surfaces must be dry and free from dust, grease and loose particles. Cracks and other irregularities must be repaired in advance.

• First painting

After brushing and cleaning the surface apply one coat of SILICOR diluted with 20% of water, before applying the final coat without dilution. As alternative to the thinned coat you can apply PRIMÁRIO BARBOLITE diluted with 5% of Diluente 1425 or ISOLANTE ISOCRIL diluted with 50% of Diluente 1425.

• Recoat

Remove dust and loose paint and then paint like a first coat. If the surface is contaminated with fungi and/or algae, disinfect the surface with SOLUÇÃO DE LIMPEZA BLOCHOQUE and then paint like a first painting.

- Environmental conditions

Ambient temperature – Above 5 °C
Relative humidity – Below 80%
Substrate humidity – Below 5%
Substrate temperature – 2 to 3 °C above dew point

APPLICATION INSTRUCTIONS

- Product preparation

Stir until fully homogenised.

- Application processes

Brush or special roller.

- Thinning and thinners

Dilute with water up to 20% for 1st coat and no dilution for 2nd coat.

- Drying time between coats

6 hours minimum.

- Cleaning thinner

Water.

STORAGE STABILITY

Minimum Temperature – 5 °C
Maximum Temperature – 35 °C

CERTIFICATES AND TESTS

Compliant with NF P902-501 and NF P902-507, SILICOR achieved a classification of **M1 – Non Flammable**, in fire reaction tests conducted by INEGI.

Note:

The paint should be first spread in a limited area and then the roller should be passed horizontally and vertically in order to achieve an uniform aspect. The last roller passage should be done smoothly from bottom to the top. Application under rainy weather, high humidity, too cold, too hot, or too windy weather should be avoided

RISKS AND SAFETY

See safety data sheet at www.barbot.pt

December 2015
