

BARBOSOFT

WATER-BASED, SEMI-MATT PAINT, FOR INTERIORS

Ref.: 1210

TECHNICAL IDENTIFICATION

Water-based paint based on vinyl copolymers, pigments and selected fillers.

AREA OF USE

Intended for painting interior render when an easily washable and semi-matt finish is required.

PROPERTIES

- Excellent wash resistance.
- Good resistance to alkalinity.
- Very easy to apply.
- Silky to the touch.
- Good coverage.
- Odourless.
- Film protected against fungal growth.

PHYSICAL CHARACTERISTICS

(Referring to White)

- Colour	See catalogue.
- Features of dry film	Semi-matt.
- Volume solids	35 ± 2%
- Practical coverage	12 to 16 m ² / L / coat.
- Drying time	2 to 4 hours.
- Volatile Organic Compounds (VOC)	EU limit value for this product (Cat. A/a): 30 g/L (2010). This product contains max. 29 g/L VOC.*

APPLICATION CONDITIONS

- Preparation of surface

Surfaces to be painted must be completely dry and free from dust, grease and loose particles. Cracks and other irregularities must be repaired in advance.

• First painting

After brushing and cleaning the surface, apply BARBOSOFT. On highly absorbent surfaces, apply ready-to-use WATER-BASED SEALANT or WHITE WATER-BASED PRIMER or BARBOPRIMER diluted with 10% of water or BARBOLITE HYDRO PRIMER diluted up to 5% with water is recommended.

• Recoat

Remove dust and loose paint and then paint like a first coat. If the surface is contaminated with fungi, disinfect the surface with BIOCHOQUE CLEANING SOLUTION and then paint like a first coat.

- Environmental conditions

Ambient temperature – Above 5 °C
Relative humidity – Below 80%
Substrate humidity – Below 5%
Substrate temperature – 2 to 3 °C above dew point

APPLICATION INSTRUCTIONS

- Product preparation

Stir until fully homogenised.

- Application processes

Brush or short-pile roller.

- Solvents and dilution ratio

Dilute with water up to 10% in the 1st coat and up to 5% in the following coats.

- Drying time between coats

4 hours minimum.

- Cleaning solvent

Water.

STORAGE STABILITY

Minimum Temperature – 5 °C
Maximum Temperature – 35 °C

CERTIFICATES AND TESTS

Compliant with NF P902-501 and NF P902-507, BARBOSOFT, achieved a classification of M1 – Non-flammable, in fire reaction tests conducted by INEGI.

RISKS AND SAFETY

See safety data sheet at www.barbot.pt

April 2016

(replaces January 2013 specifications)

The characteristics of this product may be altered without prior notice due to the continuous research and development policy at Barbot – Indústria de Tintas, S.A. This information is based on our current knowledge of the product, however since conditions of use are beyond our control, we give no guarantee of results.