

AKUA SEALING PRIMER

WATER-BASED SEALING VARNISH FOR INTERIOR FLOORS AND WOOD

Ref.: 1639

TECHNICAL IDENTIFICATION

Varnish based on water-based dispersions of special copolymers and sanding aids.

AREA OF USE

Intended for the preparation of floors for varnishing (parquet and other wooden floors), interior wood (doors, kitchen cabinets, etc.) or cork, whenever a closed-pore finish is required.

PROPERTIES

- Good filling of wood pores.
- Quick drying.
- Easy sanding.
- Easy application.
- Controls surface absorption.

PHYSICAL CHARACTERISTICS

- Colour	Colourless
- Features of dry film	Matt
- Volume solids	39 ± 2%
- Practical coverage	8 to 12 m ² /L
- Drying time	
Dust	
Touch dry	30 minutes
Sanding	2 hours minimum
- Volatile Organic Compounds (VOC)	EU limit value for this product (Cat. A/e): 130 g/L (2010). This product contains max. 50 g/L VOC.*

APPLICATION CONDITIONS

- | | |
|------------------------------|---|
| - Surface preparation | Surfaces must be completely dry and free from dust and grease. It is advisable to sand the wood in order to ensure good penetration of the AKUA SEALING PRIMER. |
| - Ambient conditions | Ambient temperature – Above 5 °C
Relative humidity – Below 80%
Substrate humidity – Below 5%
Substrate temperature – 2 to 3 °C above dew point. |
-

APPLICATION INSTRUCTIONS

- | | |
|--------------------------------------|---|
| - Product preparation | Stir well before using to homogenise the sanding aids. |
| - Application process | Brush, sprayer or short-pile roller. |
| - Thinners and dilution ratio | Dilute up to 10% with water. |
| - Recommended finishes | Water-based varnishes for wood. |
| - Drying time between coats | 2 hours minimum. The surface should be sanded before applying the top-coat varnish. |
| - Cleaning product | Water. |
-

STORAGE STABILITY

Minimum Temperature – 5 °C
Maximum Temperature – 35 °C

RISKS AND SAFETY

See safety data sheet at www.barbot.pt

August 2017

The characteristics of this product may be altered without prior notice due to the continuous research and development policy at Barbot – Indústria de Tintas, S.A. This information is based on our current knowledge of the product, however since conditions of use are beyond our control, we give no guarantee of results.

Page 2 of 2