

BARBOLUX GLOSS WOOD

VARNISH FOR INTERIOR AND EXTERIOR WOOD

Ref.: 4011

TECHNICAL IDENTIFICATION

Varnish based on alkyd resins.

AREA OF USE

Intended for varnishing interior and exterior wood in construction work, excluding resinous wood such as iroko, etc.

PROPERTIES

- Good filling qualities.
- Good hardness and elasticity.
- Easy application.
- High gloss.

PHYSICAL CHARACTERISTICS

- Colour	Colourless
- Features of dry film	Gloss finish
- Volume solids	55 ± 2%
- Practical coverage	12 to 14 m ² /L
- Drying time	
Touch dry	12 hours
For sanding	24 hours minimum
- Volatile Organic Compounds (VOC)	EU limit value for this product (Cat. A/e): 400 g/L (2010). This product contains max. 400 g/L VOC.*

APPLICATION CONDITIONS

- Surface preparation

The surface must be completely dry and free from dust and grease.

• New wood

In interiors, after sanding the wood, a prior application of AKUA SEALING PRIMER is recommended, followed by two coats of BARBOLUX GLOSS WOOD. For exterior use, sand and apply directly 3 coats of BARBOLUX GLOSS WOOD after sanding the wood.

• Previously varnished wood

Surfaces in a good condition must be sanded with fine grade sandpaper before applying BARBOLUX GLOSS WOOD. If the surface is severely damaged, first remove all the existing varnish and then treat as new wood.

- Ambient conditions

Ambient temperature – Above 5 °C
Relative humidity – Below 80%
Substrate humidity – Below 5%
Substrate temperature – 2 to 3 °C above dew point

APPLICATION INSTRUCTIONS

- Product preparation

Stir until fully homogenised.

- Application process

Brush.

- Thinners and dilution ratio

Dilute up to 5% with synthetic thinner.

- Number of coats

Apply 3 coats of varnish when used outdoors.

- Cleaning product

Synthetic or cellulose solvent.

STORAGE STABILITY

Minimum Temperature – 5 °C
Maximum Temperature – 35 °C

RISKS AND SAFETY

See safety data sheet at www.barbot.pt

August 2017

The characteristics of this product may be altered without prior notice due to the continuous research and development policy at Barbot – Indústria de Tintas, S.A. This information is based on our current knowledge of the product, however since conditions of use are beyond our control, we give no guarantee of results.

Page 2 of 2