

## BARBOLUX SATIN WOOD

VARNISH FOR INTERIOR AND EXTERIOR WOOD

Ref.: 4023

### TECHNICAL IDENTIFICATION

Varnish based on alkyd resins.

### AREA OF USE

Intended for varnishing interior and exterior wood in construction work, excluding resinous wood such as iroko, etc.

### PROPERTIES

- Good filling qualities.
- Good hardness and elasticity.
- Easy application.

### PHYSICAL CHARACTERISTICS

- Colour	Colourless
- Features of dry film	Satin finish
- Volume solids	52 ± 2%
- Practical coverage	12 to 14 m <sup>2</sup> /L
- Drying time	
Touch dry	12 hours
Recoat	24 hours minimum
- Volatile Organic Compounds (VOC)	EU limit value for this product (Cat. A/e): 400 g/L (2010). This product contains max. 400 g/L VOC.*



---

## APPLICATION CONDITIONS

---

**- Surface preparation**

The surface must be completely dry and free from dust and grease.

---

**•New wood**

In interiors, after sanding the wood, a prior application of AKUA SEALING PRIMER is recommended, followed by two coats of BARBOLUX SATIN WOOD. For exterior use, sand and apply directly 3 coats of BARBOLUX SATIN WOOD after sanding the wood.

---

**•Previously varnished wood**

Surfaces in a good condition must be sanded with fine grade sandpaper before applying BARBOLUX SATIN WOOD. If the surface is severely damaged, first remove all the existing varnish and then treat as new wood.

---

**- Ambient conditions**

Ambient temperature – Above 5 °C  
Relative humidity – Below 80%  
Substrate humidity – Below 5%  
Substrate temperature – 2 to 3 °C above dew point

---

## APPLICATION INSTRUCTIONS

---

**- Product preparation**

Stir well before using to homogenise the matting agent.

---

**- Application process**

Brush.

---

**- Thinners and dilution ratio**

Dilute up to 3% with synthetic thinner.

---

**- Cleaning product**

Synthetic or cellulose solvent.

---

## STORAGE STABILITY

---

Minimum Temperature – 5 °C  
Maximum Temperature – 35 °C

---

## RISKS AND SAFETY

---

See safety data sheet at [www.barbot.pt](http://www.barbot.pt)

---

**August 2017**

---

The characteristics of this product may be altered without prior notice due to the continuous research and development policy at Barbot – Indústria de Tintas, S.A. This information is based on our current knowledge of the product, however since conditions of use are beyond our control, we give no guarantee of results.

Page 2 of 2